

ERTALON 6SA – wytłaczany - PA6 EX



Opis:

Poliamid ten charakteryzuje się wysoką sztywnością, wytrzymałością mechaniczną, zdolnością tłumienia drgań oraz odpornością na ścieranie. Poszczególne rodzaje poliamidów tylko w niewielkim stopniu różnią się właściwościami. Po przetwórstwie termoplastycznym w stanie suchym materiał ten jest. W momencie wchłonięcia wilgoci z powietrza lub moczenia w wodzie staje się bardziej rozciągliwy i odporniejszy na ścieranie. PA ma dobre właściwości poślizgowe, nie jest wrażliwy na zabrudzenia oraz działanie chemikaliów. Nieдомieszkowany jest obojętny fizjologicznie, zatem może z powodzeniem być stosowany w przemyśle spożywczym.

Właściwości:

- duża twardość, udarność oraz ciągliwość nawet w niskich temperaturach,
- bardzo wysoka odporność na zużycie cierne,
- dobre właściwości ślizgowe powiązane z wysoką wytrzymałością na ścieranie,
- dobre właściwości ślizgowe w parach ze stalą lub POM,
- duża zdolność tłumienia drgań,
- efekt Slip – Stick (poślizg wsteczny),
- duża odporność na dynamiczne obciążenia,
- wysoka odporność na działanie rozpuszczalników, płynnych paliw oraz smarów, słaba odporność chemiczna na działanie stężonych kwasów oraz utlenionych środków,
- bardzo dobra obróbka wiórowa,
- obojętność fizjologiczna (możliwość stosowania w bezpośrednim kontakcie z produktami żywnościovymi),
- wysoka odporność na prądy pełzające.

Zastosowanie:

- koła prowadzące
- rolki transporterów
- rolki napinaczy
- koła napędowe i bierne
- koła pasowe i łańcuchowe
- blaty pod wykrojniki

- elementy uszczelnień mechanicznych
- tuleje dystansowe

Physical properties (indicative values ■)

PROPERTIES	Test methods	Units	VALUES
Colour	-	-	natural (white)/black
Density	ISO 1183-1	g/cm ³	1.14
Water absorption:			
- after 24/96 h immersion in water of 23 °C (1)	ISO 62	mg	86 / 168
	ISO 62	%	1.28 / 2.50
- at saturation in air of 23 °C / 50 % RH	-	%	2.6
- at saturation in water of 23 °C	-	%	9
Thermal Properties (2)			
Melting temperature (DSC, 10 °C/min)	ISO 11357-1/-3	°C	220
Glass transition temperature (DSC, 20 °C/min) - (3)	ISO 11357-1/-2	°C	-
Thermal conductivity at 23 °C	-	W/(K.m)	0.28
Coefficient of linear thermal expansion:			
- average value between 23 and 60 °C	-	m/(m.K)	90 x 10 ⁻⁵
- average value between 23 and 100 °C	-	m/(m.K)	105 x 10 ⁻⁵
Temperature of deflection under load:			
- method A: 1.8 MPa	+ ISO 75-1/-2	°C	70
Max. allowable service temperature in air:			
- for short periods (4)	-	°C	160
- continuously: for 5,000 / 20,000 h (5)	-	°C	85 / 70
Min. service temperature (6)	-	°C	-40
Flammability (7):			
- "Oxygen Index"	ISO 4589-1/-2	%	25
- according to UL 94 (3 / 6 mm thickness)	-	-	HB / HB
Mechanical Properties at 23 °C (8)			
Tension test (9):			
- tensile stress at yield / tensile stress at break (10)	+ ISO 527-1/-2	MPa	80 / -
	++ ISO 527-1/-2	MPa	45 / -
- tensile strength (10)	+ ISO 527-1/-2	MPa	80
- tensile strain at yield (10)	+ ISO 527-1/-2	%	4
- tensile strain at break (10)	+ ISO 527-1/-2	%	> 50
	++ ISO 527-1/-2	%	> 100
- tensile modulus of elasticity (11)	+ ISO 527-1/-2	MPa	3300
	++ ISO 527-1/-2	MPa	1425
Compression test (12):			
- compressive stress at 1 / 2 / 5 % nominal strain (11)	+ ISO 604	MPa	31 / 59 / 87
Charpy impact strength - Unnotched (13)	+ ISO 179-1/1eU	kJ/m ²	no break
Charpy impact strength - Notched	+ ISO 179-1/1eA	kJ/m ²	5.5
Ball indentation hardness (14)	+ ISO 2039-1	N/mm ²	150
Rockwell hardness (14)	+ ISO 2039-2	-	M 85
Electrical Properties at 23 °C			
Electric strength (15)	+ IEC 60243-1	kV/mm	25
	++ IEC 60243-1	kV/mm	16
Volume resistivity	+ IEC 60093	Ohm.cm	> 10 ¹⁴
	++ IEC 60093	Ohm.cm	> 10 ¹²
Surface resistivity	+ IEC 60093	Ohm	> 10 ¹³
	++ IEC 60093	Ohm	> 10 ¹²
Relative permittivity ϵ_r : - at 100 Hz	+ IEC 60250	-	3.9
	++ IEC 60250	-	7.4
- at 1 MHz	+ IEC 60250	-	3.3
	++ IEC 60250	-	3.8
Dielectric dissipation factor tan δ : - at 100 Hz	+ IEC 60250	-	0.019
	++ IEC 60250	-	0.13
- at 1 MHz	+ IEC 60250	-	0.021
	++ IEC 60250	-	0.06
Comparative tracking index (CTI)	+ IEC 60112	-	600
	++ IEC 60112	-	600

Note: 1 g/cm³ = 1,000 kg/m³; 1 MPa = 1 N/mm²; 1 kV/mm = 1 MV/m.

Legend:

- + : values referring to dry material
- ++ : values referring to material in equilibrium with the standard atmosphere 23 °C / 50 % RH (mostly derived from literature)

- (1) According to method 1 of ISO 62 and done on discs $\varnothing$ 50 mm x 3 mm.
- (2) The figures given for these properties are for the most part derived from raw material supplier data and other publications.
- (3) Values for this property are only given here for amorphous materials and not for semi-crystalline ones.
- (4) Only for short time exposure (a few hours) in applications where no or only a very low load is applied to the material.
- (5) Temperature resistance over a period of 5,000/20,000 hours. After these periods of time, there is a decrease in tensile strength - measured at 23 °C - of about 50 % as compared with the original value. The temperature values given here are thus based on the thermal-oxidative degradation which takes place and causes a reduction in properties. Note, however, that the maximum allowable service temperature depends in many cases essentially on the duration and the magnitude of the mechanical stresses to which the material is subjected.
- (6) Impact strength decreasing with decreasing temperature, the minimum allowable service temperature is practically mainly determined by the extent to which the material is subjected to impact. The value given here is based on unfavourable impact conditions and may consequently not be considered as being the absolute practical limit.
- (7) These estimated ratings, derived from raw material supplier data and other publications, are not intended to reflect hazards presented by the material under actual fire conditions. There is no 'UL File Number' available for Ertalon 6 SA stock shapes.
- (8) The figures given for the properties of dry material (+) are for the most part average values of tests run on test specimens machined out of rods $\varnothing$ 40 - 60 mm. Except for the hardness tests, the test specimens were then taken from an area mid between centre and outside diameter, with their length in longitudinal direction of the rod (parallel to the extrusion direction).
- (9) Test specimens: Type 1 B
- (10) Test speed: 50 mm/min [chosen acc. to ISO 10350-1 as a function of the ductile behaviour of the material (tough or brittle)]
- (11) Test speed: 1 mm/min
- (12) Test specimens: cylinders $\varnothing$ 8 mm x 16 mm
- (13) Pendulum used: 4 J
- (14) Measured on 10 mm thick test specimens (discs), mid between centre and outside diameter.
- (15) Electrode configuration: $\varnothing$ 25 / $\varnothing$ 75 mm coaxial cylinders; in transformer oil according to IEC 60296; 1 mm thick test specimens.
Please note that the electric strength of Ertalon 6 SA black can be considerably lower than the figure listed in the table which refers to natural material.

■ This table, mainly to be used for comparison purposes, is a valuable help in the choice of a material. The data listed here fall within the normal range of product properties. However, they are not guaranteed and they should not be used to establish material specification limits nor used alone as the basis of design.